

Icema™ R 145/88

Type of Product Moisture curing one component polyurethane adhesive.

Product Characteristics

- solvent free
- sag resistant
- low foaming
- short open time

Typical Applications Different kinds of assembly work.

Suitable substrates Galvanised or treaded steel, anodized or coated aluminium, non-ferrous metals, thermosetting plastics, HPL, GRP, rigid PVC, PS, ABS. Wood and cemented materials. Concrete and tiles.

Typical Properties

Property	Value
Base	Polyurethane
Colour	white
Density at 20°C	approx. 1.50 g/cm ³
Viscosity at 20°C	approx. 140 000 mPa.s
Shelf life	12 months

Application Instructions

- Application temperature: at least +10°C
According to type of application use: 150 – 300 g/m²
Open time (at +20°C, 50% relative humidity):
- without spraying of water: approx. 5 minutes
 - after spraying of water: approx. 2 minutes

General:

This adhesive cross links in the presence of moisture to form a solid, permanently elastic film. The water in the ambient air and parts to be bonded may already be sufficient for this process. In normal cases water is sprayed. Analyses on the influence of temperature and humidity on the strength of a completely cured glue should be carried out with respect to the specific application.

More moisture and higher temperatures accelerate the cross-linking process and therefore influences the shelf life, open- and curing time of the adhesive.

The times indicated in this data sheet are therefore only guidelines, which may vary according to the existing conditions.

Special attention:

Carbon dioxide forms during the curing reaction so that the adhesive foams to a varying degree, depending on the amount applied, the type of bond, the temperature and the pressure exerted. This property is desired for many applications and is a special advantage of this adhesive. In certain individual applications foaming may however be disadvantageous or exclude this type of adhesive. The foam developing in the glue joint, when bonding together porous materials, normally penetrates the underground quite independently of the processing viscosity. This also holds true for EPS foam, as long as the adhesive still features a processing viscosity of less than 8 000 mPa.s (+20°C). Homogeneous penetration is no longer guaranteed for higher viscosities. Visible bulges may very likely form on the top layer. The bonding of dense materials, e.g. aluminium sheet with extruded polystyrene foam, there is generally the liability of bulges to appear, as the foaming adhesive cannot expand freely. A possible solution are ventilation slots, cutting 1 – 2 mm deep into the rigid-foam.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

© and ™ are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: *by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.*

Application Instructions**Instructions for Application:**

This adhesive is applied onto one side.

Following methods are suitable for application:

- toothed trowel
- cartridge or tubular bag
- nozzle with drum unloader

Addition of Moisture:

To accelerate curing and gain independence from the varying degrees of moisture available, a fine spray of water is applied. The water is sprayed onto the applied adhesive. In some cases, the opposite side may also be sprayed.

Usually 2 – 5% of the applied adhesive is sufficient.

Assembling and Pressing:

The parts may be assembled and pressed immediately after applying the adhesive and spraying it with water. This must take place within the open wet time. The parts should continue to be pressed until the adhesive has cured to ensure the closest contact of the bonding surface.

The amount of pressure required, and the type of pressing process employed is largely determined by the type and size of the parts to be bonded, since the adhesive itself does not require pressure in order to cure and the pressure only serves to hold the bonding parts together. The pressing times required are completely dependent on substrate, temperature and degree of moisture available.

Exact times for the applications must be individually determined, as they may vary due to existing conditions. Ask for our advice on this.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

© and ™ are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.



Cleaning Instructions Please contact your local Sales Office for available cleaning solutions.

Typical Packaging Please contact your local Sales Office for available packaging options.

Storage Conditions In original sealed packaging protected from sun, dust, moisture and high temperatures. Clean and dry conditions above -25°C and below +35°C.

Disposal Advice Please refer to the MSDS for disposal instructions.

Safety Advice Please refer to the MSDS for safety advice.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

© and ™ are trademarks of H.B. Fuller Company ("H.B. Fuller") or one of its affiliated entities.

NOTE TO USER: *by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.*

